Industrial Equipment - Warning/Instructional Marking Gloss Topcoated White Polyester - Conventional Printing

Warning and instructional labels contain critical information about how to properly operate industrial equipment as well as the hazards associated with improperly operating the equipment. It is crucial that the information conveyed on these important labels remain legible for the life of the product. Pressure- sensitive films are ideal because they are rigid and provide excellent printability, keeping the label intact and legible. Film also provides good resistance to the abrasion that occurs during product assembly, shipment, and use. Pressure- sensitive adhesives are specially formulated to securely bond to a large variety of challenging surfaces. To prevent product misuse and consumer liability, look no further than pressure-sensitive films and adhesives to protect your brand identity. For more information on FLEXcon's pressure-sensitive film solutions for warning/instructional markings, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX000375



This image is an example of how FLEXcon products may be used

Product:

DPM[®] Poly White Sheet

Benefits:

- 2.0 mil gloss white polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Topcoated surface is compatible with most conventional and UV ink systems (we recommend evaluating the intended ribbon and ink system for compatibility with the product under the application conditions)
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass

- Backed with a layflat 90 lb. moisture stable polycoated release liner ideal for sheet-form converting
- UL recognized under UL 969 UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component
- CSA accepted under CSA File No. 99214



DPM[®] Poly White Sheet

| | 21.11 | | |
|---------------------------------|--|-----------------------------|---|
| PRODUCT DATA | VALUE | | TEST METHOD |
| Physical Properties | | | |
| Thickness (Mils[microns]) | Film | 2.0 (51) +/- 10% | ASTM D 3652 (Modified for use with |
| | Adhesive | 0.9-1.0 (23-25) +/- 0.1 (3) | non-tape products) |
| | Liner | 6.9 (175) +/- 10% | |
| Dimensional Stability (%) | No Shrinkage Observed | | Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C) |
| Adhesion Properties | | | |
| Ultimate Peel from | Average | | ASTM D 903 (Modified for 72 hour dwell |
| | Oz/In | (N/m) | time) |
| ABS | 60 | (660) | |
| Acrylic | 68 | (748) | |
| Acrylic Powder Paint | 47 | (517) | |
| Aluminum | 54 | (594) | |
| Epoxy Powder Paint | 62 | (682) | |
| Glass | 56 | (616) | |
| HDPE | 32 | (352) | |
| Painted Metal | 49 | (539) | |
| Polycarbonate | 58 | (648) | |
| Polyester | 87 | (957) | |
| Polyester Powder Paint | 15 | (165) | |
| Polypropylene | 12 | (132) | |
| Polyurethane Powder Paint | 54 | (594) | |
| Stainless Steel | 55 | (605) | |
| Styrene | 54 | (594) | |
| Expected Shear | | | ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load |
| Room Temp (hours) | 25 | | |
| Tack (gm/sq cm) | 360 | | ASTM D 2979 |
| Expected Exterior Life | Two years | | |
| Service Temperature Range | -40°F to 302°F (-40°C to 150°C) | | |
| Minimum Application Temperature | 50°F (10°C) | | |
| Storage Stability | Two years when stored at 70°F (21°C) and 50% relative humidity | | |

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 10/27/2011



FLEXCON 1 FLEXcon Industrial Park, Spencer, MA 01562-2642, Telephone (508) 885-8300 FAX (508) 885-8301 www.FLEXcon.com